

	<b>Product Technical Information</b>	Number	IT.010
		Date of issue	22.11.2017
		Version	4.0
		Damp insulation	

## Membrane of the elastomer for horizontal damp insulation of buildings AlphaHP Ultra

1. **Technical specifications:** PN-EN 14909:2012, Flexible sheets for waterproofing – Plastic and rubber damp proof courses – Definitions and characteristics
2. **Manufacturer/Place of production:** Alpha Dam Sp. z o.o., 87-207 Dębowa Łąka 45, Poland
3. **Description of product:** Single-layer membrane of elastomer
4. **Purpose and range of applications:** The purpose of damp proof courses is to prevent water rising up all from the ground, water moving from one part of a wall to another and to deflect water from an inner wall of a cavity wall construction to the exterior of the building.
5. **Method of placement:** between the foundation wall and the aboveground part of the building, also under the concrete screed between the parts of the building structure.
6. **Information for the user:**
  - Placement conditions:  
An AlphaHP Ultra membrane placement should be carried out under conditions, which enable normal masonry work. Placements should not be carried out at temperatures below -5 °C.
  - Use conditions:  
A damp-proofing with AlphaHP Ultra membranes should be carried out according to a technical project prepared in compliance with valid building code.
  - Bonding:  
The AlphaHP Ultra parts should be bond by pressure welding with hot air. A bonding with a polymer EPDM adhesive is also possible. When using both methods there should be an overlap of minimum 5 cm in width.
  - Storage:  
Before the use at construction site an AlphaHP Ultra membrane should be stored in its original packing protected against solar radiation.
7. **Information on the CE marking:**



In accordance with the requirements ensuing from the standard PN-EN 14909:2012.

	<b>Product Technical Information</b>	Number	IT.010
		Date of issue	22.11.2017
		Version	4.0
		Damp insulation	

#### 8. Product characteristics:

Essential characteristics	Unit	Performance
Visible defects	-	None
Length	m	20 or 25 (0% to +5%)
Width	m	0,06 – 0,60 (-0,5% to +1%)
Straightness	mm	≤ 75/10 m
Thickness	mm	0,750 (±5%)
Mass	kg/m <sup>2</sup>	0,707 (-±4,5%)
Watertightness	2kPa Method A	watertight
Resistance to static loading	kg	≥ 20
Durability - after artificial aging process - after exposure to alkalis	2 kPa Method A	watertight
Resistance to tearing (nail shank) - longitudinal lap joint - transverse lap joint	N N	100 100
Resistance to impact	mm Method A	≥ 2000
Joint strength - longitudinal lap joint - transverse lap joint	N/50 mm N/50 mm	≥134 ≥ 139
Resistance to low temperature	°C	≤ -30
Reaction to fire	class	E
Resistance to effects of asphalt (watertightness)	40 kPa	watertight
Danger substances	-	none

For the producer signed (s):



Proxy Iwona Majek

Dębowa Łąka, 22 November 2017